

Muralo Adhesium 8050 Heavy Duty Vinyl Paste

| | |
|-----------------------------|---|
| Description: | Adhesium 8050 is a top quality ready to use heavy duty vinyl adhesive designed for the installation of commercial weight vinyl wallcovering and mylar. This high solids, low water content, adhesive has superior holding power and excellent initial tack. Preferred by both professionals and amateurs because it is easy to use, hold seams tight, odorless, non-staining, non-flammable and mildew resistant. 8050 cleans up with water. |
| Recommended Uses: | Can be used to hang all types of wallcovering including commercial weight vinyls or mylars, light and medium vinyl and foils. |
| Surface Preparation: | <p>Clean surface to be hung and make sure it is free of all contaminants, including mildew. Fill and repair cracks or holes with Muralo Spackle[®] brand of surfacing compound or Synkoloid's Spackling Paste. Glossy surface should be dulled and given a coat of 8400 Adhesium Vinyl Primer or 8500 Oil Base Primer.</p> <p>Previously painted flat should be given a coat of 8400 Vinyl Primer or 8500 Oil Base Primer to insure adhesion.</p> <p>Unpainted wallboard should be given a coat of 8500 Oil Base Primer to insure subsequent release. Previously hung vinyl wallcovering that is firmly bonded should be coated with Adhesium 8400 Vinyl Primer.</p> |
| Application: | <p>Follow wallcovering manufacturers instructions and good paper hanging methods. Use paste as is.</p> <p>Apply paste in a uniform manner, making sure no dry spots are left. Use a brush or a medium nap (3/8") roller. Remove all excess adhesive from the face of the wallcovering with clear water and sponge. Temperature should be at least 50°F when applied. Keep adhesive tightly sealed when not in use. Store between 60°F to 80°F for easiest application.</p> |
| Open Time: | 30 minutes to one hour depending upon porosity of wallcovering, condition of wall, temperature and other variables |
| Weight/Gal: | 10.6 + 0.1 |

Revised 2/2/2004

| | | |
|------------------------------|---|-----------------|
| Viscosity: | 1700 – 2200 poise | |
| High Shear Viscosity: | 2.5 poise max | |
| Freeze Thaw: | Protect from freezing | |
| Color: | Off White | |
| Solids: | 43 – 44% by weight | |
| Flash point: | None to boil | |
| Clean-UP: | Soap and water | |
| Coverage: | Approximately 200 sq. ft. per gallon or 6 to 8 rolls | |
| Packaging: | Per Case | Weight |
| | Quarts | 6 18 lbs |
| | ½ Gallons | 6 35 lbs. |
| | Gallons | 4 47 lbs. |
| | 2 Gallons | Pail 24 lbs. |
| | 5 Gallons | Pail 57 lbs. |
| VOC/VOS: | Contains 2.7 lbs./gal. VOS or 335 gms/ltr. VOC | |
| Cautions: | Keep out of reach of children.. Do not take internally. Use adequate ventilation. Keep from freezing. | |

DISCLAIMER:

The information contained herein is presented in good faith. This information is furnished without warranty of any kind. Employers should use this information only as a supplement to other information gathered by them and must take independent determination of suitability and completeness of information from all sources to assure proper use of these Materials and the safety and health of employees. Any use of this data and information must be determined by the user to be in accordance with applicable federal, state and local laws and regulations.

NOTICE: Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. Exposure to lead dust or fumes may cause adverse health effects, especially in children or pregnant women.

Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup.

For additional information, contact the USEPA/Lead information Hotline at 1-800-LEAD-FYI.